

Laminated Opaque Vinyl

Part #	15-000261 (SC-2), 15-000261W (SC-2W), 15-000261G (SC-2G), 15-000261BK (SC-2BK), 15-000361 (SC-3), 15-000361B (SC-3B), 15-000361R (SC-3R)														
Colors	Yellow (SC-2), White (SC-2W) , Gray (SC-2G), Black (SC-2BK), Green (SC-3), Blue (SC-3B), Red (SC-3R)														
Thickness	14 mils														
Finished Square Yard Weight	13 oz														
Roll Size	61"W x 100 yds														
Base Material	Woven 10x9 count 1000/1000 denier polyester scrim.														
Construction	Polyester weft lock scrim completely laminated between two layers of flame-retardant PVC (vinyl)														
Strength Tensile	<table border="0"> <thead> <tr> <th><u>Warp (lb.)</u></th> <th><u>Fill (lb.)</u></th> </tr> </thead> <tbody> <tr> <td>240</td> <td>185</td> </tr> <tr> <td>90</td> <td>100</td> </tr> </tbody> </table> <p>(Per Fed. Test Std. 191, Method 5136)</p>	<u>Warp (lb.)</u>	<u>Fill (lb.)</u>	240	185	90	100								
<u>Warp (lb.)</u>	<u>Fill (lb.)</u>														
240	185														
90	100														
Mullen Burst	240 lb. / sq. in.														
Product Characteristics	Resists most acids, flame, water, grease, rot, mildew, & ultra-violet. Very tear resistant.														
Flame Resistance	<p>Meets or exceeds requirements of the following flame resistance tests:</p> <table border="0"> <thead> <tr> <th><u>Organization</u></th> <th><u>Test</u></th> </tr> </thead> <tbody> <tr> <td>Federal Test Std. (GSA)</td> <td>191A, Method 5903</td> </tr> <tr> <td>California Fire Marshall</td> <td>Section 137.1 (small scale)</td> </tr> <tr> <td>Underwriters Labs</td> <td>UL-217 (small scale)</td> </tr> <tr> <td>National Fire Protection</td> <td>701 (small scale)</td> </tr> <tr> <td>ASTM</td> <td>E-84 Class A</td> </tr> <tr> <td>MVSS</td> <td>302</td> </tr> </tbody> </table>	<u>Organization</u>	<u>Test</u>	Federal Test Std. (GSA)	191A, Method 5903	California Fire Marshall	Section 137.1 (small scale)	Underwriters Labs	UL-217 (small scale)	National Fire Protection	701 (small scale)	ASTM	E-84 Class A	MVSS	302
<u>Organization</u>	<u>Test</u>														
Federal Test Std. (GSA)	191A, Method 5903														
California Fire Marshall	Section 137.1 (small scale)														
Underwriters Labs	UL-217 (small scale)														
National Fire Protection	701 (small scale)														
ASTM	E-84 Class A														
MVSS	302														
Flame Retardant Agent	Antimony Oxide (Under normal use, vinyls will quickly self-extinguish when any external source of flame is removed.														
Temperature Limits	Service Range (ambient) of -10° to +160°F														